

AQUA SEAL®

CHEMICAL GROUT SPECIFICATIONS

TEST TYPE	RESULTS	TEST METHOD
Density (core)	Free rise 3 lbs/ft3 Confined 15 lbs/ft3	ASTM D-1622
Low Temperature Aging (-20 deg. F) (Shrinkage)	0% 0%	ASTM D-2126 1 Day 7 Days
Water Absorption	<1%	ASTM D-2127
Shear Strength	50 PSI	ASTM C-273
Tensile Strength	75 PSI	ASTM D-1623
Elongation	5%	ASTM D-1623
Viscosity	@400 cps "B" side	200 cps "A" side
% Solids	100	
Color	Amber	
Reaction Time	3-5 seconds	
K-Factor	.123	
Yield Point	40/45	ASTM D-1621
Compressive Strength	45 P.S.I.	ASTM D-1621

NOTE: AQUA SEAL® is a two component hydrophobic polyurethane.
Spec data may vary on actual jobsite conditions.
Aqua Seal contain no solvents, no V.O.C., no CFC's.

Sealing Systems, Inc.

9350 County Road 19*Loretto, MN *55357 *Telephone 763-478-2057*Toll Free 800-478-2054 *Fax 763-478-8868